


**TOSHIBA**

# Fine Ceramics





**We wish to be one of the sustainers  
of the affluent future.  
Our minute materials can help  
a big dream come true.**



**We are pioneers aiming to be the industry leaders.  
We answer the needs of the age with quality "Only-one" products.**

We began developing silicon nitride ( $\text{Si}_3\text{N}_4$ ) ceramics in the 1960 s, and by providing numerous products to industries such as bearings, automobiles, and semiconductors, we have supported the foundations of various industries and the evolution of cutting edge technology. By using rare earth oxides, especially yttria ( $\text{Y}_2\text{O}_3$ ), as a sintering agent for silicon nitride ( $\text{Si}_3\text{N}_4$ ), we succeeded in creating tough fine ceramics. Many highly reliable and high quality products are used in space and aircraft engine bearings and power module boards such as IGBTs, and have received high praise.

**I  
N  
D  
E  
X**

**Fine Ceramics for Electronics**  
Silicon nitride ( $\text{Si}_3\text{N}_4$ ) ceramics

Typical values for properties of fine ceramics for electronics— **4**

Plain substrates ( $\text{Si}_3\text{N}_4$ )— **5,6**

Active metal brazed layer copper (AMC) substrates— **7**

**Engineering ceramics**  
Silicon nitride ( $\text{Si}_3\text{N}_4$ ) ceramics

Typical values for properties of engineering ceramics— **8**



Silicon nitride ( $\text{Si}_3\text{N}_4$ ) bearing balls— **9**

Silicon nitride ( $\text{Si}_3\text{N}_4$ ) ceramics for automobiles— **10**

# Fine Ceramics for Electronics

## Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) ceramics

Fine ceramic substrates with high thermal conductivity are becoming indispensable components under the circumstances needs for high power, high integration, slim and lightweight, high frequency and environmental friendliness prevail. We take advantage of one of our core technologies, the grain boundary control of ceramic microstructure, to produce the silicon nitride (Si<sub>3</sub>N<sub>4</sub>) substrates with the world highest thermal conductivity on a commercial basis.




### Typical values for properties of fine ceramics for electronics

Item	Measuring method	Unit		Silicon nitrides (Si <sub>3</sub> N <sub>4</sub> )		
				TSN-90		
Density	JIS Z8807	RT	Mg/m <sup>3</sup>	3.35		
Thermal properties	Specific heat	JIS C2141	J/kg·K	650		
	Thermal conductivity	JIS R1611	W/m·K	90		
	Coefficient of thermal expansion	JIS C2141	RT-500°C	x10 <sup>-6</sup> /K	3.4	
Electrical properties	Dielectric strength	JIS C2110-1	50Hz	kV/mm	25.0	
	Volume resistivity	JIS C2141	RT	Ω·m	1x10 <sup>15</sup>	
	Dielectric constant	JIS C2141	1MHz		8.0	
	Dielectric factor	JIS C2141	1MHz	tanδx10 <sup>-4</sup>	8.0	
Mechanical properties	3-point bending strength	JIS C2141	RT	MPa	680	
	Fracture toughness	JIS R1607	RT	MPa·m <sup>1/2</sup>	6.5	
	Young's modulus	JIS R1602	RT	GPa	300	
	Poisson's ratio	JIS R1602			0.27	
Features				High thermal conductivity High strength		
Main applications				Substrates for semiconductor assembly Radiator plates (for compression force) Heatsinks		

The values in the table are reference values, not guaranteed values.

## Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) plain substrates

Toshiba Materials' silicon nitride plain substrates utilize material technology and sintering technology cultivated over many years to achieve a dense and fine structure, and have excellent mechanical properties and high thermal conductivity. Silicon nitride's coefficient of thermal expansion is close to that of Si chips, making it ideal as a substrate for semiconductor mounting, and meeting the diverse needs of our customers.




### Standard design

Item	Unit	Silicon nitride (Si <sub>3</sub> N <sub>4</sub> )
		TSN-90
Outer dimensions	mm	MAX 170x130
	Tolerance	±0.15 (Laser cut)
Thickness	mm	0.32
	Tolerance	±0.05mm
Warp	mm/mm	0.4% Under (≤50mm)
Surface area	—	Blast processing (Honing)


Values on the chart are standard design rule and not guaranteed value.  
Please contact us for possibility of corresponding to designs not covered in above chart.

### Temperature dependency of thermal conductivity and coefficient of thermal expansion




BeO, Al<sub>2</sub>O<sub>3</sub> and Si are other companies' products.


In order to meet further needs for highly reliable semiconductor mounting substrates, we were quick to recognize excellent mechanical performances of silicon nitrides. As a result, we have taken the lead in the world in commercializing high thermal conductive silicon nitride insulated substrates for power semiconductors with more than four times thermal conductivity, which had been as low as alumina, while maintaining high strength. Our high thermal conductive silicon nitride substrates are increasingly being used for PCUs (Power Control Units) of EVs (Electric Vehicles) and HEVs (Hybrid Electric Vehicles).



**Comparison of thermal resistance (example)**



**Comparison of deflection characteristics of plain substrates**




## Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) Active Metal brazed layer Copper (AMC) substrates

We offer all purpose copper plated ceramic substrates by active metal brazing method to meet diversified requirements that have arisen in power module substrates.

Active metal brazed copper (AMC) substrates are made by joining copper circuit plate onto ceramic substrates by brazing. They are suitable for making fine patterned power module circuits with high thermal cycle performance. We offer silicon nitride AMC (SIN-AMC) substrates for the basement ceramic substrates.

AMC substrates are best fit for high power semiconductor module substrates such as power transistor substrates like IGBTs. They directly dissipate heat with sufficient insulation.




### [Characteristics of SIN-AMC substrates]

- Simple structure with low thermal resistance. Specifically, thermal resistance of SIN-AMC substrate with the thickness of 0.32mm is almost equivalent to that of ALN-AMC substrate with the thickness of 0.635mm.
- Excellent mechanical strength properties; They have high thermal cycle performance even if the copper circuit is made thick (up to 0.8mm) to lower thermal resistance and increase power output.
- Their high fracture toughness allows direct ultrasonic bonding of electrode terminals onto the copper circuit plate and securing the substrate onto heatsink by rivets.
- Coefficient of thermal expansion equivalent to that of ceramics substrates enables direct mounting of Si chips onto the copper circuit plate.
- High joint strength of copper circuit plate
- High voltage resistance

### [Applications]

- Power transistor module (IGBT, MOSFET, etc.)



### Standard design

Type of ceramics		Silicon Nitride (Si <sub>3</sub> N <sub>4</sub> )		
A, B	Ceramic dimension	Maximum effective area 90 x 110		
	Tolerance	±0.15		
C	Ceramic thickness	0.25/0.32		
	Tolerance	±0.05		
Electrode material		Cu		
D	Cu thickness	0.1~0.4	0.5~0.6	0.7~0.8
E	Insulation distance	≥0.5	≥0.7	≥1.0
F	Pattern dimension	≥0.5	≥0.7	≥1.0
G	Insulation distance	≥0.4	≥1.0	≥1.2
H	Taper dimension	≥0.5D (Less than 1/2 of the Cu)		

Values on the chart are standard design rule and not guaranteed value.



Please contact us for possibility of corresponding to designs not covered in above chart.

# Engineering ceramics

## Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) ceramics

Among many ceramic materials, namely zirconia, silicon carbide and alumina, which are known to be used as engineering fine ceramics, we persistently produce silicon nitride ceramics as the only material for engineering ceramics. We have well understood excellent properties such as high thermal conductivity and high strength of nitride ceramics from early-stages of the research. Then we have developed a grain boundary control technology and applied it to make Silicon nitride ceramics into stable, high-performance, high-functional materials and components. Silicon nitride ceramics will show their well-balanced mechanical properties under high-speed rotation, high-speed sliding and high vacuum as they have good abrasion resistance, good corrosion resistance, insulation, heat resistance, etc. We are looking forward to meet customer's diversified requirements with our silicon nitride ceramics.

### High performances of silicon nitride ceramics



### Typical values for properties of engineering ceramics

Items	Measuring method	Unit		Silicon nitrides (Si <sub>3</sub> N <sub>4</sub> )			
				TSN-03	TSN-08	TSN-23	
Density	JIS Z8807	RT	Mg/m <sup>3</sup>	3.23	3.27	3.27	
Hardness	JIS R1601	HV(20kgf)		1,500	1,600	1,500	
Mechanical and thermal properties	Threepoint bending strength	RT	MPa	1,000	1,000	900	
		1000°C	MPa	750	900	700	
		1200°C	MPa	450	850	400	
	Compression strength		RT	MPa	5,000	4,500	4,000
	Young's modulus	JIS R1602	RT	GPa	308	308	313
	Poisson's ratio	JIS R1602			0.29	0.29	0.28
	Fracture toughness	ASTM F2094	RT	MPa · m <sup>1/2</sup>	6~8	6~8	5~7
	Specific heat	JIS R1611		J/kg · K	680	680	680
	Thermal conductivity	JIS R1611		W/m · K	20	20	25
Coefficient of thermal expansion	JIS R1618	RT-800°C	x10 <sup>-6</sup> /K	3.0	3.0	3.0	
Thermal shock temperature difference		(ΔTc)	°C	800	900	700	
Electrical properties	Dielectric strength	JIS C2110-1	50Hz	kV/mm	>14	>14	>14
	Volume resistivity	JIS C2141	RT	Ω · m	>10 <sup>12</sup>	>10 <sup>12</sup>	>10 <sup>12</sup>
Corrosion* resistance	Acid			Good	Good	Good	
	Alkali			Good	Good	Good	
Features				High strength Abrasion resistant	Heat resistant Abrasion resistant	Abrasion resistant Corrosion resistant (Electrical corrosion)	
Recommendatory applications				Bearings Engine parts Mechanical parts	Mechanical parts Refractory tools Heat-resistant and abrasion-resistant parts	Bearings Engine parts	

\*Corrosion resistances were measured under following conditions.

Acid; 96 hours immersion at RT in 36% HCl, 95% H<sub>2</sub>SO<sub>4</sub> and 60% HNO<sub>3</sub> Alkali; In 5% NaOH and 40% NaOH

The values in the table are reference values, not guaranteed values.



## Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) Bearing Balls

We offer light-weight, high strength, high rigidity and high abrasion resistant silicon nitride (Si<sub>3</sub>N<sub>4</sub>) ceramics for structural parts. They are especially fit for bearing balls and applied to various lines of industrial use.




### Comparison of properties between silicon nitride (Si<sub>3</sub>N<sub>4</sub>) ceramics and high carbon chrome bearing steels; and features of ceramic bearings

Item	Unit	Silicon nitrides	Bearing steels (SUJ)	Features of ceramic bearings
Thermal resistance	°C	800	180	Heavy-duty bearings under elevated temperature
Density	Mg/m <sup>3</sup>	3.24	7.8	Low centrifugal force to rolling balls, causing long life and low temperature rising
Coefficient of thermal expansion	x10 <sup>-6</sup> /K	3.0	12.5	Minimum dimensional deviation in inner clearances by temperature rising, causing low vibration and small change in pressurization
Hardness	Hv (20kgf)	1500	750	Minimum deformation in rolling contact members, causing high rigidity
Young's modulus	GPa	308	208	
Poisson's ratio		0.29	0.3	
Corrosion resistance		Good	Not good	Serviceable under chemical environments including acidic and alkaline solutions
Magnetism		Nonmagnetism	Ferromagnetic material	Minimum rotational fluctuation made by magnetization under strong magnetic field
Electric conductivity		Insulator	Conductor	No electric corrosion especially in generators and motors
Mode of bonding		Covalent bonding	Metallic bonding	Minimum adhesion of contact parts caused by oil film breaking

The values in the table are reference values, not guaranteed values.

### Results of load withstanding test for various ceramics



Courtesy of JTEKT Corporation

## Silicon nitride ( $\text{Si}_3\text{N}_4$ ) ceramics for automobiles

Silicon nitride ceramics, which are lighter than conventional metal parts, have high wear resistance, and have excellent corrosion resistance, were jointly developed in 1987 with Cummins Engine, the largest diesel engine manufacturer in the United States at the time, and it has been adopted for wear-resistant parts of the fuel system of diesel vehicles. Today, it is also used in parts of common rail systems for diesel fuel injection equipment.

Recently, silicon nitride ceramic balls, which have excellent wear resistance, have been adopted as a countermeasure against electrolytic corrosion of bearings used in electric vehicle (EV) motors, and are used as materials that can contribute to environmental problems.

By fusing "product technology" and "material technology" cultivated over 30 years in this way, we will provide products with excellent cost performance.



Bearing of motor for electric vehicle (EV)

## RESTRICTIONS ON PRODUCT USE

Toshiba Corporation and its subsidiaries and affiliates are collectively referred to as “TOSHIBA”. Hardware, software and systems described in this document are collectively referred to as “Product”.

- TOSHIBA reserves the right to make changes to the information in this document and related Product without notice..
- This document and any information herein may not be reproduced without prior written permission from TOSHIBA. Even with TOSHIBA's written permission, reproduction is permissible only if reproduction is without alteration/omission.
- Though TOSHIBA works continually to improve Product's quality and reliability, Product may be subject to characteristic changes, damage, or malfunction due to changes in the environment, such as temperature or atmosphere. Customers are responsible for complying with safety standards and for providing adequate designs and safeguards for their hardware, software and systems which minimize risk and avoid situations in which characteristic change, damage and malfunction of Product could cause loss of human life, bodily injury or damage to property. Before customers use the Product, create designs including the Product, or incorporate the Product into their own applications, customers must also refer to and comply with (a) the latest versions of all relevant TOSHIBA information, including without limitation, this document, the specifications, and the data sheets and (b) the instructions for the application with which the Product will be used with or for. Customers are solely responsible for all aspects of their own product design or applications, including but not limited to (a) determining the appropriateness of the use of this Product in such design or applications; (b) evaluating and determining the applicability of any information contained in this document, or in charts, diagrams, programs, or any other referenced documents; and (c) validating all operating parameters for such designs and applications. TOSHIBA ASSUMES NO LIABILITY FOR CUSTOMERS' PRODUCT DESIGN OR APPLICATIONS.
- PRODUCT IS NEITHER INTENDED NOR WARRANTED FOR USE IN EQUIPMENTS OR SYSTEMS THAT REQUIRE EXTRAORDINARILY HIGH LEVELS OF QUALITY AND/OR RELIABILITY, AND/OR A MALFUNCTION OR FAILURE OF WHICH MAY CAUSE LOSS OF HUMAN LIFE, BODILY INJURY, SERIOUS PROPERTY DAMAGE AND/OR SERIOUS PUBLIC IMPACT ("UNINTENDED USE"). Except for specific applications as expressly stated in this document, Unintended Use includes, without limitation, equipment used in nuclear facilities, equipment used in the aerospace industry, lifesaving and/or life supporting medical equipment, equipment used for automobiles, trains, ships and other transportation, traffic signaling equipment, equipment used to control combustions or explosions, safety devices, elevators and escalators, and devices related to power plant. IF YOU USE PRODUCT FOR UNINTENDED USE, TOSHIBA ASSUMES NO LIABILITY FOR PRODUCT. For details, please contact your TOSHIBA sales representative or contact us via our website.
- Do not disassemble, alter, modify, translate or copy Product, whether in whole or in part.
- Product shall not be used for or incorporated into any products or systems whose manufacture, use, or sale is prohibited under any applicable laws or regulations.
- The information contained herein is presented only as guidance for Product use. No responsibility is assumed by TOSHIBA for any infringement of patents or any other intellectual property rights of third parties that may result from the use of Product. No license to any intellectual property right is granted by this document, whether express or implied, by estoppel or otherwise.
- ABSENT A WRITTEN SIGNED AGREEMENT, EXCEPT AS PROVIDED IN THE RELEVANT TERMS AND CONDITIONS OF SALE FOR PRODUCT, AND TO THE MAXIMUM EXTENT ALLOWABLE BY LAW, TOSHIBA (1) ASSUMES NO LIABILITY WHATSOEVER, INCLUDING WITHOUT LIMITATION, INDIRECT, CONSEQUENTIAL, SPECIAL, OR INCIDENTAL DAMAGES OR LOSS, INCLUDING WITHOUT LIMITATION, LOSS OF PROFITS, LOSS OF OPPORTUNITIES, BUSINESS INTERRUPTION, AND (2) DISCLAIMS ANY AND ALL EXPRESS OR IMPLIED WARRANTIES AND CONDITIONS RELATED TO SALE, USE OF PRODUCT, OR INFORMATION, INCLUDING WARRANTIES OR CONDITIONS OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, ACCURACY OF INFORMATION, OR NONINFRINGEMENT.
- Do not use or otherwise make available Product or related software or technology for any military purposes, including without limitation, for the design, development, use, stockpiling or manufacturing of nuclear, chemical, or biological weapons or missile technology products (mass destruction weapons). Product and related software and technology may be controlled under the applicable export laws and regulations including, without limitation, the Japanese Foreign Exchange and Foreign Trade Law and the U.S. Export Administration Regulations. Export and re-export of Product or related software or technology are strictly prohibited except in compliance with all applicable export laws and regulations.
- Please contact your TOSHIBA sales representative for details as to environmental matters such as the RoHS compatibility of Product. Please use Product in compliance with all applicable laws and regulations that regulate the inclusion or use of controlled substances, including without limitation, the EU RoHS Directive. TOSHIBA ASSUMES NO LIABILITY FOR DAMAGES OR LOSSES OCCURRING AS A RESULT OF NONCOMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS.

# Toshiba Materials Co., Ltd.

## Overseas Sales & Marketing Department

1-1, Shibaura 1-Chome, Minato-ku, Tokyo 105-8001, Japan

Tel: +81-3-3457-4874 Fax: +81-3-5444-9235

<http://www.toshiba-tmat.co.jp/eng/index.htm>

---

■ **Toshiba America Electronic Components, Inc. [Advanced Materials Division]**

1 Cabot Rd Suite 120, Hudson, MA 01749, U.S.A.

TEL: +1-508-303-5041 FAX: +1-978-567-0719

■ **Toshiba Electronics Europe GmbH**

Hansaallee 181 40549 Dusseldorf Germany

TEL: +49-211-5296-0 FAX: +49-211-5296-400

■ **Toshiba Electronics Asia (Hong Kong), Ltd.**

Level 11, Tower 2, Grand Century Place, No. 193 Prince Edward Road West, Mongkok, Kowloon, Hong Kong

TEL: +852-2375-6111 FAX: +852-2375-0969

■ **Toshiba Electronics Asia (Singapore) Pte. Ltd.**

20 Pasir Panjang Road, #12-25/26 Mapletree Business City, Singapore 117439

TEL: +65-6278-5252 FAX: +65-6271-5155

■ **Toshiba Devices & Storage (Shanghai) Co., Ltd.**

**Shanghai Head Office**

10F, Raffles City, No.268, Xizang Road(M), Huangpu District, Shanghai, 200001, China

TEL: (21) 6060-6555

Products Agency